



TEST REPORT

No. : XMIN1502000775ML

Date : Feb 12, 2015

Page: 1 of 3

CUSTOMER NAME: XIAMEN SOLAR FIRST ENERGY TECHNOLOGY CO.,LTD
ADDRESS: 17TH FLOOR, BUILDING NO.3, XINGLINWAN BUSINESS OPERATION
CENTER, JIMEI DISTRICT, XIAMEN CITY, P.R.CHINA

The following sample(s) was/ were submitted and identified on behalf of the client as:

Sample Name : BEAM
Product Specification : 1800
Manufacturer : Xiamen Solar First Energy Technology Co.,Ltd
Buyer : Xiamen Solar First Energy Technology Co.,Ltd
Material and Mark : AL6005-T5
Other Information : SF-GM-B01
Date of Receipt : Feb 05, 2015
Testing Start Date : Feb 05, 2015
Testing End Date : Feb 12, 2015
Test result(s) : For further details, please refer to the following page(s)

Signed for
SGS-CSTC Standards Technical
Services Co., Ltd Xiamen Branch
Testing Center

Spike Tang
Authorized signatory



This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To check the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755) 8307 1443, or email: CN.Doccheck@sgs.com

SGS-CSTC Standards Technical Services Co., Ltd.
Xiamen Branch

No.31 Xianghong Road, Xiang'an Torch Industrial Zone, Xiamen, Fujian Province, China. 361101 t (86-592) 5761588 f (86-592) 5765380 www.sgs.com.cn
中国·福建·厦门·火炬(翔安)产业区翔虹路31号 邮编:361101 t (86-592) 5761588 f (86-592) 5765380 e sgs.china@sgs.com

TEST REPORT

No. : XMIN1502000775ML

Date : Feb 12, 2015

Page: 2 of 3

Bend test:

Test method: according to the client's requirements, as the following schematic, place the sample on two supports with the mid-length match the former, load the force vertically till the sample destroyed.


Determine the maximum force.

Former: width is 30mm; length is 105mm,

Span length: 1000mm;


Test rate: 12mm/min.

The test schematic:



Test result: The maximum bend force is 16265N.

Test curve:



TEST REPORT

No. : XMIN1502000775ML

Date : Feb 12, 2015

Page: 3 of 3

Test Photo:



Photo 1: before loading




Photo 2: the moment of destruction



Photo 3: destroyed part



Photo 4: sample after test

***** End of Report *****